

Technisches Datenblatt

Technical Data Sheet

PE-Klebeband allwetter grünlich/ adhesive PE tape all weather greenish

Eigenschaft Property	Prüfmethode Test method	Einheit Unit	Allgemeine Daten und Werte General Data and Value
Dicke/ Thickness	AFERA 4006	µm	150
Eigenschaft Property	Prüfmethode Test method	Einheit Unit	Erfahrungswerte ¹ Typical Values ¹
Bruch-/Reißdehnung Stress at break	AFERA 4005	%	300
Reißkraft Force at break	AFERA 4004	N/cm	24
Schälfestigkeit Stahl/ peel resistance steel	AFERA 4001	N/cm	3

RKW Agri GmbH & Co. KG

Rosbacher Weg 5
D-64720 Michelstadt / Germany

Phone +49 (0) 6061 77 - 0
Fax +49 (0) 6061 77 - 209
www.rkw-group.com

¹ Die Angaben sind typische Erfahrungswerte, beziehen sich nicht auf ein konkretes Produkt und sind nicht Bestandteil eines Angebots. Für die Leistung des Produkts wird weder eine ausdrückliche noch eine stillschweigende Gewähr oder Garantie übernommen, da die Art und Weise der Verwendung und Handhabung nicht unserer Kontrolle unterliegt.

Lagerung: bei 10-30°C in der Originalverpackung 12 Monate haltbar

¹ The values are typical experience values, do not relate to a specific product and are not part of any offer. No warranty or guarantee expressed or implied is made regarding the performance of the product, since the manner of use and handling is beyond our control.

Storage: in the original packaging for 12 months under 10-30°C